

ACCREDITATION Standards Council of Canada, Registration #1.

REGISTRATION ISO 9001:2000, registered by QMI, Registration #001109.

SPECIFICATIONS OF ORDER

Determine flame resistance in accordance with the CAN/ULC-S109-03 Small and Large Flame Tests, as per our Quotation No. 08-002-5158 accepted May 12, 2008.

IDENTIFICATION

One reinforced material identified as: "CC-ICT" 1st Sample.
(Bodycote sample identification number 08-002-S0435-1)

TEST RESULTS

CAN/ULC-S109-03 Small-Flame Test
Standard Methods of Tests for Flame-Resistant Textiles and Films

Tested "as received"

		Damaged Length (mm)	Flaming Dripping (s)	Afterflame Time (s)	
Direction 1	1:	125	0.0	2.5	
	2:	127	0.0	1.1	
	3:	135	0.0	4.0	
	4:	112	0.0	2.3	
	5:	130	0.0	6.1	
Direction 2	6:	138	0.0	1.8	
	7:	140	0.0	1.6	
	8:	138	0.0	1.8	
	9:	146	0.0	2.7	
	10:	143	0.0	1.3	
Average:		133	-	-	
Maxima Specified by ULC-S109 Small Flame Test:		165	-	-	(average)
		190	2.0	-	(individual)